

GEOCONN-TS

OD	PPF	WT	ID	Drift Dia.	Collapse			Internal yield pressure			Minimum Yield Load (for Regular Coupling)		
					J55 K55	L80 N80	P110	J55 K55	L80 N80	P110	J55 K55	L80 N80	P110
mm	Kg/m	mm	mm	mm	MPa	MPa	MPa	MPa	MPa	MPa	Ton	Ton	Ton
114.30	15.63	5.69	102.92	99.75	27.7	34.1	38.3	33.0	48.1	66.1	75	109	150
	17.26	6.35	101.60	98.43	34.2	43.8	52.3	36.9	53.7	73.7	83	121	167
	18.75	6.88	100.53	97.36	39.5	51.7	63.5	40.0	58.1	79.9	90	131	180
	20.09	7.37	99.57	96.39	44.3	58.9	73.7	42.8	62.2	85.6	96	139	192
	22.47	8.56	97.18	94.01	52.6	76.4	98.9	49.7	72.3	99.4	110	160	220
127.00	22.32	7.52	111.96	108.79	38.3	50.0	61.0	39.3	57.2	78.6	109	159	219
	26.79	9.19	108.61	105.44	51.0	72.3	92.9	48.1	69.9	96.1	132	192	264
139.70	23.07	6.99	125.73	122.56	27.9	34.4	38.8	33.2	48.3	66.4	113	164	226
	25.30	7.72	124.26	121.08	33.9	43.4	51.6	36.7	53.4	73.4	124	180	248
	29.76	9.17	121.36	118.19	45.7	60.9	76.6	43.6	64.1	87.2	146	212	291
	34.23	10.54	118.62	115.44	52.9	77.0	100.3	50.1	72.8	100.2	166	241	331
152.40	27.98	7.72	124.26	121.08	28.6	35.5	40.5	33.7	48.9	67.2	136	198	272
	32.74	9.65	133.10	129.92	43.0	57.0	71.0	42.1	61.2	84.1	168	244	335
	36.46	10.16	132.08	128.91	46.8	62.6	79.0	44.3	64.3	88.5	176	256	352
168.28	29.76	7.32	153.64	150.47	20.5	23.9	27.8	28.8	42.0	57.7	143	208	287
177.80	34.23	8.05	161.70	158.52	22.6	26.4	30.6	30.1	43.7	60.1	166	242	333
	38.69	9.19	159.41	156.24	29.9	37.3	43.0	34.3	49.9	68.7	189	274	377
	43.16	10.36	157.07	153.90	37.3	48.5	58.8	38.7	56.3	77.4	211	307	422
	47.62	11.51	154.79	152.40	44.6	59.4	74.3	43.0	62.5	85.9	233	339	465
	52.09	12.65	152.50	149.33	50.1	70.2	89.9	47.2	68.7	94.4	254	370	509
	56.55	13.72	150.37	147.19	54.0	78.6	104.3	51.2	74.5	102.4	274	399	548
193.68	39.29	8.33	177.01	173.84	19.9	23.4	27.0	28.6	41.5	57.1	188	274	376
	44.20	9.53	174.63	171.45	27.0	33.0	36.9	32.6	47.5	65.3	213	310	427
	50.15	10.92	171.83	168.66	35.2	45.2	54.3	37.4	54.5	74.9	243	354	486
	58.04	12.70	168.28	165.10	45.6	60.8	76.4	43.5	63.3	87.0	280	407	560
219.08	35.72	6.71	205.66	202.49	9.4	9.9	9.9	20.3	29.6	40.6	173	252	346
	41.67	7.72	203.63	200.46	13.0	14.9	15.2	23.4	34.1	46.8	199	289	397
	47.62	8.94	201.19	198.02	17.4	21.0	23.6	27.1	39.4	54.2	229	333	457
	53.58	10.16	198.76	195.58	23.8	28.3	32.3	30.8	44.8	61.6	258	376	517
244.48	53.58	8.94	226.59	222.63	13.9	16.3	17.0	24.3	35.3	48.6	256	373	512
	59.53	10.03	224.41	220.45	17.7	21.3	23.9	27.2	39.7	54.5	286	416	572
	64.74	11.05	222.38	218.41	22.4	26.3	30.5	30.0	43.7	60.0	314	457	628
	69.95	11.99	220.50	216.54	26.8	32.8	36.6	32.6	47.4	65.1	339	494	678
	79.62	13.84	216.79	215.90	35.4	45.7	54.8	37.6	54.7	75.2	388	565	777
250.83	93.46	15.88	219.08	215.11	43.0	57.0	70.9	42.0	61.1	84.0	454	660	908
273.05	67.71	10.16	252.73	248.77	14.4	17.0	18.0	24.7	35.9	49.4	325	473	647 *
	75.90	11.43	250.19	246.23	18.7	22.2	25.2	27.8	40.4	55.6	364	529	725 *
	82.60	12.57	247.90	243.94	27.5	27.7	31.8	30.6	44.5	61.1	399	580	793 *
	90.33	13.84	245.36	241.40	28.7	35.6	40.6	33.7	49.0	67.3	437	635	869 *
	105.66	16.51	240.03	236.07	39.8	52.1	64.1	40.1	58.4	80.3	515	750	1,026 *
339.72	81.11	9.65	320.42	316.46	7.8	7.9	7.9	18.8	27.4	37.7	388	564	560 *
	90.78	10.92	317.88	313.92	10.6	11.5	11.5	21.3	31.0	42.7	437	636	631 *
	101.20	12.19	315.34	311.38	13.4	15.6	16.1	23.8	34.6	47.7	486	707	702 *
	107.15	13.06	313.61	311.15	15.3	18.4	19.9	25.5	37.1	51.0	519	755	750 *

* : Joint Strength , not yield load

Legal Notice
 The use of this information is at the reader/user's risk and no warranty is implied or expressed by Metal One Corporation or its parents, subsidiaries or affiliates (herein collectively referred to as "Metal One") with respect to the use of information contained herein. The information provided on this Data Sheet is for informational purposes only, and was prepared by reference to engineering information that is specific to the subject products, without regard to safety-related factors, all of which are the sole responsibility of the operators and users of the subject connectors. Metal One assumes no responsibility for any errors with respect to this information.

Statements regarding the suitability of products for certain types of applications are based on Metal One's knowledge of typical requirements that are often placed on Metal One products in standard well configurations. Such statements are not binding statements about the suitability of products for a particular application. It is the customer's responsibility to validate that a particular product with the properties described in the product specification is suitable for use in a particular application. The products described in this Data Sheet are not recommended for use in deep water offshore applications. For more information, please refer to http://www.mtlo.co.jp/mo-con/_images/top/WebsiteTerms_Active_20333287_1.pdf the contents of which are incorporated by reference into this Data Sheet.